


SPATORELLA GIPS



Unit of measurement	Pieces/Pallet	Consumption	Color/other specifications
5 kg/bag 15 kg/sack	4 pcs/box 80 pcs/pallet	- 1 kg/m ²	white -



SPATORELLA GIPS

Stucco for filling joints between gypsum-board panels.

TECHNICAL FEATURES

- Gypsum-based stucco, composed of hydrated lime, marble powder of selected granulometry and special additives.
- Gypsum-based stucco, used together with the covering tapes to stucco joints between gypsum-board tiles, to stucco joints and cracks in finished concrete surfaces, to stucco concrete surfaces with or without porosity.
- To realize finishes in gypsum-based supports and in gypsum panels.
- It is characterized by an excellent workability, effortless opening and non-slip, which facilitates the application in vertical surfaces.
- For indoor environments.
- Easily rubbed with sandpaper.
- In conformity with EN 132791.

AREA OF APPLICATION

- It is used together with the covering tapes to stucco joints between gypsum-board tiles, to stucco joints and cracks in finished concrete surfaces.
- To stucco concrete surfaces with or without porosity.



TECHNICAL DATA

Form	Powder
Color	White
Storage	12 months in original packaging and in a dry place
Combustibility	Incombustible
Mixing ratio	7.5-8 liters of water per 25 kg Gypsum Spatorella
Pot life	1.5-2 hours
pH of the mixture	12
Application temperature	from +5°C to +35°C
Maximal thickness for one layer	1 mm
Standby for rubbing	after 24 hours
Standby for painting	after 3-4 weeks

FINAL DATA

Resistance to compression according to EN 1015-11	≥ 3,5 N/mm ²
Flexural resistance according to EN 1015-11	≥ 1.9 N/mm ²
Adhesion strength in gypsum according to EN 1015-12	≥ 0.5 N/mm ²

