


SPATORELLA



Unit of measurement	Pieces/Pallet	Consumption	Color/other specifications
15 kg/sack 5 kg/bag	80 pcs/pallet 4 pcs/box	1 kg/m ² 1 kg/m ²	white -



Plaster stucco for smooth finishes.

TECHNICAL FEATURES

- Plaster stucco, composed of white cement, hydrated lime, white marble powder, resins and special additives.
- Characterized by good workability and easy opening; without vertical slip, thus facilitating application in vertical surfaces.
- Used for indoor and outdoor environments
- Allows a thickness from 1 up to 3 mm for every layer.
- Easily rubbed with sandpaper and provides a solid and smooth finishing
- It is in conformity with EN 998 – 1 norm.

AREA OF APPLICATION

- It is used to stucco walls and ceiling filled with traditional mortar or pre-prepared lime and cement- based mortar.
- It is used to stucco concrete surfaces.
- It is used to stucco gypsum-board walls and ceiling.

IMPORTANT NOTES

- Do not add other materials such as lime or cement in the given product.
- Do not apply the product on painted surfaces.
- Do not apply the product on supports of plastic coatings.
- Do not apply it in a thickness bigger than 5 mm.
- Do not add water in the mixture, after the mixture has been prepared.
- Apply it in temperatures from +5°C to +10°C.

Reinforcement with Latex

To improve the adhesiveness, resistance to water, plasticity, flexibility, mechanical strength, etc., SPATORELLA can be reinforced with Latex additive.

The mixing ratio is 1: 5 with water.

Mixture Preparation

Mix 15 kg plaster stucco with 4.5 - 5 liters of water with an electric low-rotation mixer, until you get a homogeneous mixture. It is recommended to let the acquired mixture settle for about 5 minutes, and then stir it again before use.

PREPARATION OF SUPPORT

Supports that are characterized by a greater unevenness than 3mm, should be leveled before the application of stucco. The support where the product will be applied should be free of external materials, such as: grease, varnishes, paints, etc. the support should be watered before the application of the product.

MANNER OF PRODUCT APPLICATION

The product is opened on the surface through a smooth spatula, thus ensuring a full opening and coverage of the surface. The product is applied in a thickness of 3mm, in one or two layers.

CLEANING

The cleaning of work tools and hands should be done before the product is completely dried.

CONSUMPTION

Approximately 1kg/ m²

PACKAGING

SPATORELLA is packaging in 25 Kg paper bag.

SEHLF-LIFE STORAGE

12 months after manufacture date, if stored in original and unopened packaging and protected from direct exposure to sun and frost.



TECHNICAL DATA (IN + 23°C AND 50% U.R.)

Form	Powder
Color	White
Storage	12 months in original packaging and in a dry place
Combustibility	Incombustible
Mixing ratio	4.5 - 5 liters of water per 15 kg SPATORELA
Powder density	1.6 gr/cm ³
pH of the mixture	12
Pot life	3 - 4 hours
Application temperature	+5°C to +35°C
Maximal thickness for one layer	1mm
Standby for the second layer application	After 60 - 90 min
Standby for rubbing	24 hours
Standby for painting	3 - 4 Weeks

FINAL DATA

Resistance to compression after 28 days	≥ 4,5 N/mm ²
Flexural resistance after 28 days	≥ 1,7 N/mm ²
Adhesion strength to concrete	≥ 0,5 N/mm ²